

## VAPOR GROWTH METHOD FOR THIN SEMICONDUCTOR FILM

## VAPOR GROWTH METHOD FOR THIN SEMICONDUCTOR FILM

Patent Number: JP62091495  
Publication date: 1987-04-25  
Inventor(s): SUGAO SHIGEO  
Applicant(s): NEC CORP  
Requested Patent: ☐ JP62091495  
Application Number: JP19850230245 19851015  
Priority Number(s):  
IPC Classification: C30B25/02; C30B29/40  
EC Classification:  
EC Classification:  
Equivalents:

### Abstract

**PURPOSE:** To grow the titled thin film by adsorbing a group-III halide on a substrate crystal in an inert atmosphere, then absorbing a group-V element thereon in a reducing atmosphere, repeating the process, and controlling each growth layer at a high growth velocity.

**CONSTITUTION:** A reaction tube 1 consisting of the first chamber 12 and the second chamber 13 is provided with a substrate holder 15 to which an InP substrate 14, for example, is fixed and which can be inserted alternately into the two chambers through a bellows 19. A group-V halide (hereinafter referred to as PH<sub>3</sub>) for the second chamber and H<sub>2</sub> as a reducing gas are charged into the second chamber 13 of the reaction tube, a group-III element 17 (hereinafter referred to as metallic In) put in a quartz dish is heated by a 2-zone furnace 16 to 650-900 deg.C, and the substrate 14 is heated to 500-800 deg.C. Then N<sub>2</sub> as an inert gas, PH<sub>3</sub>, and HCl are introduced into the first chamber 12, the formed InCl<sub>3</sub> is adsorbed on the surface of the substrate 2, and then the substrate 2 is inserted into the second chamber 13 wherein PH<sub>3</sub> is adsorbed in the reducing atmosphere. Subsequently, the substrate 2 is inserted alternately into the first chamber 12 and the second chamber 13 to epitaxially grow each monoatomic layer. After a desired thickness is obtained, the substrate 2 is held in the second chamber 13 and cooled while protecting surface with PH<sub>3</sub>.